# SEMPERIT (S

## FOOD CONTACT MATERIAL

## **NR SBR A 621**

#### **General:**

NR-SBR, off-white, - PAH free sulfur crosslinked food quality not applicable for fatty foods

\*BfR XXI category 4

For commodities which as a result of their intended use come into contact with foodstuff for just a very short period of time or with a very small part of its surface; test for alcoholic (up to 10%) and acidic food \*FDA 21 Food and Drugs Part 177.2600 Rubber articles intended for repeated use in contact with aqueous foods

Wrapping: stretched foil, labelled standard finishing in talcum

\*REACH-conform in accordance with EU 1272/2013 \*PAH - meets GS cat.3 in full content

#### Working temperature range

dyn.(stat.)	max.	short-term			
-30 (-45)°C	+70°C	+90°C			
Compression set DIN ISO 815					
Temperature		CS			
	-30 (-45)°C set DIN ISO 815	-30 (-45)°C +70°C set DIN ISO 815			

+70°C

40%

#### Ageing ISO 188

22h

Conditions	Hardness	Strength	Elongation
70h / 70°C	5 Shore A	10 %	15 %

ROTACURED-SHEETS product number	thickness mm	width mm	length mm
401122100	1,00	1.400	20.000
401122200	2,00	1.400	20.000
401122300	3,00	1.400	10.000
401122400	4,00	1.400	10.000
401122500	5,00	1.400	10.000
401122600	6,00	1.400	10.000
401122800	8,00	1.400	5.000
401122000	10,00	1.400	5.000

PAH disclaimer

Referring to an international proficiency test and information received from the testing laboratories about accuracy of test results we may inform you, that test results for the same specimen from different laboratories may not correlate: \* Results of the 10 PAH with individual limits of < 1 mg/kg in the measurement range around the limit

are only accurate to approx. ± 70%. \* Results of the overall limit of < 50 mg/kg are only accurate to approx. ± 35%

Our test results are provided on an as-is basis and to the best of our knowledge, without any legally binding commitment. Our tests do not release you from own tests as to the respective application envisaged.

### **Properties:**

Hardness [Shore A]:	ISO 7619-1	65±5		
Density [g/cm <sup>3</sup> ]:	ISO 1183-1	~1,42		
Tensile Strength [N/mm <sup>2</sup> ]:	ISO 37 type 2	8		
Elongation at Break [%]:	ISO 37 type 2	380		
correspond to WDK-guideline 2201 : 2020-10 "Quality characteristics of				
Elastomer sheets- and plates"				

#### Stabilities:

non resistant non resistant non resistant non resistant moderately resistant resistant moderately resistant

#### Please note:

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operation conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether specified properties of our products are sufficient for the intended use. If there is any doubt (e.g. chemical resistance), do not hesitate to contact our qualitied engineers. The use of our products is at the user's own risk. We do not have any influence concerning the application and individual usage. We do of course warrant the quality of our products according to our General Sales Conditions, available on our website or on request. ©Copyright 2020 Semperit Technische Produkte GmbH

Subject to alteration without prior notice: In order to always have the latest product- and safety information make sure you visit our website (<u>www.semperitgroup.com</u>) regularly or contact specialist dealers or a Semperit application engineer. Additional important general information about the range, storage and tolerances can also be found at our website (<u>www.semperitgroup.com</u>) and must be followed without exception.

